



Product Data Sheet

Tenite Acetate 105E3V36327 Clear, Trsp

Application/Uses

- Ophthalmics

Product Description

Tenite cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of *Tenite* cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. *Tenite* cellulosic plastics are available in natural, clear, selected ambers or smoke transparents and black translucent. Color concentrates are available in let-down ratios from 10:1 to 40:1. *Tenite* Cellulosic Acetate 105-27 has a plasticizer level of 27%.

Typical Properties

Plasticizer		27%
Specific Gravity	D 792	1.28
<hr/>		
Tensile Stress @ Yield	D 638	33.1 MPa (4800 psi)
Tensile Stress @ Break	D 638	36.5 MPa (5300 psi)
Elongation @ Break	D 638	25%
Flexural Modulus	D 790	2137 MPa (3.1)
Flexural Yield Strength	D 790	54.5 MPa (7900 psi)
Rockwell Hardness, R Scale	D 785	82
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	187 J/m (3.5 ft·lbf/in.)
@ -40°C (-40°F)	D 256	48 J/m (0.9 ft·lbf/in.)

Deflection Temperature ^d		
@ 1.82 MPa (264 psi)	D 648	73°C (163°F)
@ 0.455 MPa (66 psi)	D 648	83°C (181°F)
Vicat Softening Temperature ^d		
	D 1525	109°C (228°F)
Water Absorption, 24 h immersion		
	D 570	2.3%
Soluble Matter Loss		
	D 570	0.3%
Weight Loss on Heating [72 hours @ 80°C (176°F)]		
	D 706	1.8%
	D 542	1.46-1.49
Light Transmission ^e		
	E 308	>90%
Haze ^e		
	D 1003	<8.5%
Specific Heat @ 23°C (73°F)		
	DSC	1.26-1.67 kJ/kg·K (0.301-0.399 Btu/lb·°F)
Thermal Conductivity		
	C 177	0.17-0.33 W/m·K (1.2-2.3)
Coefficient of Linear Thermal Expansion		
	D 696	11- /°C (mm/mm·°C) (6- /°F (in./in.·°F))
Mold Shrinkage		
	D 955	0.2-0.6%
Dielectric Strength		
	D 149	11.8-18.7 kV/mm (300-475 V/mil)
Dielectric Constant 1 MHz		
	D 150	3.3-3.8
Dissipation Factor 1 MHz		
	D 150	0.01-0.15
Volume Resistivity		
	D 257	- ohm·cm

Characteristics

Formula 105 - heat stabilized.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will

conform exactly to the values given.

27-Jun-2001 3:07:00 PM