

Ultramid® A3X2G5

Polyamide 66 (Nylon 66)



Product Description

Ultramid A3X2G5 is a 25% glass fiber reinforced injection molding PA66 grade with improved flame retardance and enhanced long-term performance. Flame retardant based on red phosphorus; outstanding mechanical and electrical properties.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm ³	1183	1.34	
Moisture, %	62		
(50% RH)		1.4	
(Saturation)		6	
RHEOLOGICAL	ISO Test Method	Dry	Conditioned
Melt Volume Rate (275 °C/5 Kg), cc/10min.	1133	40	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23°C		8,500	6,000
Tensile stress at break, MPa	527		
-40°C		196	-
23°C		140	100
Tensile strain at break, %	527		
23°C		3	4.5
IMPACT	ISO Test Method	Dry	Conditioned
Charpy Notched, kJ/m ²	179		
23°C		13	17
-30°C		10	-
Charpy Unnotched, kJ/m ²	179		
23°C		65	70
-30°C		60	65
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	260	-
HDT A, °C	75	250	-
HDT B, °C	75	250	-
Coef. of Linear Thermal Expansion, Parallel, mm/mm °C		0.3 X10 ⁻⁴	-
Coef. of Linear Thermal Expansion, Normal, mm/mm °C		0.7 X10 ⁻⁴	-
ELECTRICAL	ISO Test Method	Property Value	
Comparative Tracking Index	IEC 60112	550	
Volume Resistivity	IEC 60093	1E13	
Surface Resistivity	IEC 60093	1E13	
Dielectric Constant (1 MHz)	IEC 60250	3.7	
Dissipation Factor (1 MHz)	IEC 60250	200	
Dielectric Strength, KV/mm	IEC 60243-1	33	
UL RATINGS	ISO Test Method	Dry	Conditioned

Flammability Rating, 1.5mm	UL94	V-0
Relative Temperature Index, 1.5mm	UL746B	
Mechanical w/o Impact, °C		130
Mechanical w/ Impact, °C		115
Electrical, °C		120

Processing Guidelines

Material Handling

Max. Water content: 0.10%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80 °C (176 °F) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 285-300 °C (545-572 °F)

Mold Temperature 80-90 °C (176-194 °F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Pressures

Fast fill rates are recommended to insure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.